

SOLITEX MENTO® 5000

Heavy-weight roofing underlay



Technical data

		Material
Protective and covering fleece		Polypropylene microfibre
Functional film		Monolithic TEEE

Property	Regulation	Value
Colour		Anthracite
Surface weight	EN 1849-2	215 g/m ² ; 0.7 oz/ft ²
Thickness	EN 1849-2	0.70 mm ; 28 mils
Water vapour resistance factor μ	EN ISO 12572	114
sd value	EN ISO 12572	0.08 m
g value		0.4 MN-s/g
Vapour permeance	ASTM E 96	41 perms
Fire class	EN 13501-1	E
Outdoor exposure		6 months
Hail impact resistance	VKF / AEAI	Class HR 5
Watertight joints with 'connect' adhesive strips or TESCON VANA tape	EN 13859-1	W1
Sarking/roofing underlay membrane (Germany)	ZVDH-Produktdatenblatt 2024	USB / UDB
Suitable as temporary roof covering (Germany)	ZVDH	Yes
Water column	EN ISO 811	10 000 mm ; 32' 10"
Watertightness, non-aged/aged*	EN 13859-1	W1 / W1
Tensile strength MD/CD	EN 13859-1 (A)	350 N/5 cm / 270 N/5 cm ; 40 lb/in / 31 lb/in
Tensile strength MD/CD, aged*	EN 13859-1 (A)	330 N/5 cm / 245 N/5 cm ; 38 lb/in / 28 lb/in
Elongation MD/CD	EN 13859-1 (A)	55% / 65%
Elongation MD/CD, aged*	EN 13859-1 (A)	30 % / 40 %
Nail tear resistance MD/CD	EN 13859-1 (B)	270 N / 400 N ; 61 lbf / 90 lbf
*) Durability after artificial ageing at 120 °C ; 248 °F	EN 1297 / EN 1296	Passed
Flexibility at low temperature	EN 1109	-40 °C ; -40 °F
Temperature resistance	EN 1109, EN 1296, EN 1297	Permanent -40 °C to +120 °C; -40 °F to 248 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU-in/(h·ft ² ·°F)
CE labelling	EN 13859-1	Yes

Areas of application

For use as a diffusion-open roofing underlay over roof sheathing, MDF and wood-fibre underlay panels, and over all thermal insulation materials.

Supply forms

Art. no.	GTIN	Length	Width	Contents	Weight	Sales unit	Container
12903	4026639129031	50 m	1.5 m	75 m ²	16 kg	1	20
13759	4026639137593	50 m	3 m	150 m ²	34 kg	1	20

Advantages

- ✓ Maximal flexibility in planning construction schedules thanks to 6 months of outdoor exposure
- ✓ Well-protected building components: highly diffusion-open and maximum protection against driving rain and hail
- ✓ Dry building components: pore-free TEEE functional film actively transports moisture to the outside
- ✓ Permanent protection thanks to the high resistance to ageing and heat of the TEEE functional film
- ✓ Provides protection during the construction period: suitable as a temporary covering

General conditions

SOLITEX MENTO membranes are to be installed with the printed side facing the installation technician. The membranes are to be installed as a roofing underlay membrane horizontally (parallel to the eave) in a taut manner with no sagging. Ensure that the subsurface is even when installing the membrane as a roofing underlay membrane. When the membrane is installed as a freely hanging underlay membrane, the rafter spacing is limited to 100 cm (3 ft).

Fasteners may not be applied in areas where water runs off in a collected manner (e.g. in roof valleys).

Ridge ventilation should be provided in the case of non-insulated attics that have not been converted. To do so, install the SOLITEX membrane in such a way that it stops 5 cm (2") before the ridge. In addition, permanent ventilation fittings should be provided in the unconverted attic. The membrane should be protected against the long-term impacts of UV radiation (e.g. by darkening windows).

The SOLITEX MENTO 5000 roofing underlay can be used as temporary covering for up to 6 months to protect the building structure during the construction phase in accordance with the regulations of the Central Association of the German Roofing Trade (ZVDH); in this case, the roof pitch must be at least 14° (approx. 3:12). Other national regulations may vary. The system components TESCON NAIDECK nail-sealing tape, ORCON F adhesive sealant and TESCON VANA are to be used for sealing of overlaps and joints. The connect variant has two self-adhesive strips for reliable external sealing. The specifications of the applicable national regulations are to be taken into account when carrying out installation and adhesion.

Under the regulations of the German Roofing Trade, these membranes are suitable as an additional measure for rain protection when installed as freely hanging underlay membranes with simple overlapping underneath roof tiles; when installed over timber sheathing as an underlay membrane with simple overlapping, SOLITEX MENTO membranes are also suitable as an additional measure for rain protection in the case of more demanding requirements.

Additional instructions for blown-in insulation materials SOLITEX MENTO 5000 can also be used as a boundary layer for blown-in insulation materials of all types. It is recommended to use nail-sealing underneath the counter battens (e.g. TESCON NAIDECK). The battens must already be fitted before the blowing-in process is carried out. A protruding lath must be installed under the horizontal roof battens in the centre of the space between the rafters so that moisture occurring under the covering is drained off centrally between the rafters. This protruding lath should be at least 1 cm (3/8") thicker than the counter battens. It limits the bulging of the membranes during the blowing-in process and ensures the necessary cross-sectional area for ventilation.

If the insulation material is blown in from the outside, the blow-in holes can subsequently be taped over using TESCON VANA with a width of 15 cm (6").



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about installation and design details is available in the pro clima planning documentation. If you have any questions, please contact [pro clima Technical Support](<https://proclima.com/service/technical-support>).

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de